


Raw magnets of Samarium-Cobalt (SmCo)

Disc magnet of SmCo



Article number	Quality	D mm	H mm	Adhesive force* N	Weight g	Temperature °C	Magnetisation
MSASm4x3	RCS26H	4 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	2.5	0.3	350	axial
MSASm5x3	RCS26H	5 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	3.5	0.5	350	axial
MSASm6x3	RCS26H	6 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	4	0.7	350	axial
MSASm7x3	RCS26H	7 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	6	0.9	350	axial
RM008SCSb99rh11	RCS26H	8 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	8.5	1.3	350	axial
MSASm10x3	RCS26H	10 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	10	2	350	axial
RM011SCSb99rh00	RCS26H	11 ^{+0.1} / _{-0.1}	3,5 ^{+0.1} / _{-0.1}	12	2.8	350	axial
MSASm12x3	RCS26H	12 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	12	2.8	350	axial
RM015SCSb99rh03	RCS26H	15 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	18	4.4	350	axial
RM015SCSb99rh05	RCS26H	15 ^{+0.1} / _{-0.1}	4 ^{+0.1} / _{-0.1}	22	5.9	350	axial
RM018SCSb99rh02	RCS26H	18 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	25	6.4	350	axial
RM020SCSb99rh07	RCS26H	20 ^{+0.1} / _{-0.1}	4 ^{+0.1} / _{-0.1}	32	10	350	axial
RM024SCSb99rh02	RCS26H	24 ^{+0.1} / _{-0.1}	3 ^{+0.1} / _{-0.1}	30	11	350	axial
RM025SCSb99rh04	RCS26H	25 ^{+0.1} / _{-0.1}	4 ^{+0.1} / _{-0.1}	41	16	350	axial

PRODUCT INFORMATION:

SmCo magnets can be produced in almost every size and without tool costs. Even very small quantities are possible. The surface is blank. The specified temperature refers to the maximum operating temperature of the material. The resistance may be reduced due to the geometry.

As an alternative to our standard product we offer:

» customised dimensions

- » modified directions of magnetisation
- » other types of magnetisation
- » further qualities
- » additional coating (e.g. zinc-plated, nickel-plated, epoxy-coated)

Magnetized via the height (H)

* The forces have been determined at room temperature on a polished plate made of steel (S235JR according to DIN 10 025) with a thickness of 10 mm (1kg~10N). A deviation of up to -10% from the specified value is possible in exceptional cases. In general, the value is exceeded. The type of application (installation situation, temperatures, counter anchors, etc.) sometimes influence the forces enormously. The values given are for orientation purposes. Let our experts advise you.